

RUST-OLEUM®
INDUSTRIAL



LEAKSEAL®

The flexible rubber coating; seals leaks and cracks

- Watertight semi smooth finish
- Can be top-coated with latex or oil-based paints
- For use on metal, aluminum, PVC, concrete, masonry, asphalt roofing materials, etc.
- Overcoatable with various paints

footer_main_page_line_one

footer_main_page_line_two

POPIS PRODUKTU (DLOUHÝ)

Designed to fill and seal leaks and cracks on metal, aluminium, galvanized metal, PVC, concrete, masonry, asphalt/bituminous roofing materials, vinyl siding, fiberglass, and more.

DOPORUČENÉ POUŽITÍ

Designed to fill and seal leaks and cracks on metal, aluminium, galvanized metal, PVC, concrete, masonry, asphalt/bituminous roofing materials, vinyl siding, fiberglass, and more.

DRY_TIMES_BY_20

Dotykem suché:	20 - 30 minutes
Suché na manipulaci:	45 - 60 minutes
Suchý nátěr:	Apply second layer LeakSeal after 15 - 30 minutes. Top-coated with water-based or oil-based paints after 24 hours.
Plně vytvrzené:	24 hours

DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

65 µm

TEORETICKÁ SPOTŘEBA

0,74 m² per aerosol at 65 µm dry film thickness

PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate, size of the leakage and material losses during application.

PŘÍPRAVA POVRCHU

Remove all dirt and debris from the area to be coated. Wash area with a detergent and water solution, rinse with fresh water, and allow the surface to dry thoroughly. Remove any loose paint or previous coatings with a wire brush or sandpaper. Lightly sand glossy surfaces. Wipe the sanded surface clean when finished. Test previous coated material for compatibility before use.

PODMÍNKY POUŽITÍ

Use outdoors or in a well-ventilated area such as an open garage. Apply when temperature is between 50°F and 90°F (10 - 32°C) and humidity is below 85% to ensure proper drying. Do not apply to surfaces, when heated, exceed 200°F (93°C). Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

APLIKACE A ŘEDĚNÍ: AEROSOL

Shake aerosol vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum for technical support. A test spray on cardboard is recommended to obtain feel for the spray pattern. Hold the aerosol 8-18" (20 - 45 centimetre) from the surface and spray in short even strokes. It is recommended to apply a light first coat. Apply a second heavier coat to ensure proper coverage. A thicker film can be achieved by moving the nozzle closer to the surface. Initial spray may have some foaming or bubbling, but will dissipate as the coating dries. For best results, apply 2 coats. Allow to dry 15- 30 minutes between coats.

POZNÁMKY

- If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.
- Wipe off tip when finished.
- Clean-up wet paint with xylene or mineral spirits. Properly discard empty container.
- Do not burn or place in home trash compactor.

DOBA POUŽITELNOSTI

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu