

**RUST-OLEUM®**  
INDUSTRIAL



**LEAKSEAL®**

## The flexible rubber coating; seals leaks and cracks

- Watertight semi smooth finish
- Can be top-coated with latex or oil-based paints
- For use on metal, aluminum, PVC, concrete, masonry, asphalt roofing materials, etc.
- Overcoatable with various paints

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

## OPIS

Designed to fill and seal leaks and cracks on metal, aluminium, galvanized metal, PVC, concrete, masonry, asphalt/bituminous roofing materials, vinyl siding, fiberglass, and more.

## ZALECANE UŻYCIE

Designed to fill and seal leaks and cracks on metal, aluminium, galvanized metal, PVC, concrete, masonry, asphalt/bituminous roofing materials, vinyl siding, fiberglass, and more.

## CZAS SCHNIĘCIA PRZY 20°C/RH 50%

Na dotyk:	20 - 30 minutes
Do użytku:	45 - 60 minutes
Do przemalowania:	Apply second layer LeakSeal after 15 - 30 minutes. Top-coated with water-based or oil-based paints after 24 hours.
Pełne utwardzenie:	24 hours

## ZALECANA GRUBOŚĆ WARSTWY NA SUCHO

65 µm

## ZUŻYCIE TEORETYCZNE

0,74 m<sup>2</sup> per aerosol at 65 µm dry film thickness

## ZUŻYCIE PRAKTYCZNE

Practical coverage depends on many factors such as porosity and roughness of the substrate, size of the leakage and material losses during application.

## PRZYGOTOWANIE POWIERZCHNI

Remove all dirt and debris from the area to be coated. Wash area with a detergent and water solution, rinse with fresh water, and allow the surface to dry thoroughly. Remove any loose paint or previous coatings with a wire brush or sandpaper. Lightly sand glossy surfaces. Wipe the sanded surface clean when finished. Test previous coated material for compatibility before use.

## WARUNKI APLIKACJI

Use outdoors or in a well-ventilated area such as an open garage. Apply when temperature is between 50°F and 90°F (10 - 32°C) and humidity is below 85% to ensure proper drying. Do not apply to surfaces, when heated, exceed 200°F (93°C). Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

## APLIKACJA I ROZCIĘCZANIE: AEROSOL

Shake aerosol vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum for technical support. A test spray on cardboard is recommended to obtain feel for the spray pattern. Hold the aerosol 8-18" (20 - 45 centimetre) from the surface and spray in short even strokes. It is recommended to apply a light first coat. Apply a second heavier coat to ensure proper coverage. A thicker film can be achieved by moving the nozzle closer to the surface. Initial spray may have some foaming or bubbling, but will dissipate as the coating dries. For best results, apply 2 coats. Allow to dry 15- 30 minutes between coats.

## UWAGI

- If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.
- Wipe off tip when finished.
- Clean-up wet paint with xylene or mineral spirits. Properly discard empty container.
- Do not burn or place in home trash compactor.

## OKRES TRWAŁOŚCI PRODUKTU

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Data wydania: 07/02/2025

**Dostępne kolory i opakowania:** Więcej informacji na temat dostępnych kolorów i opakowań na stronie internetowej [www.rust-oleum.eu](http://www.rust-oleum.eu).

**Zrzeczenie się:** Informacje tu zawarte przekazywane są w dobrej wierze, bez udzielania gwarancji. Ponieważ warunki aplikacji są poza naszą kontrolą, Rust-Oleum nie może ponosić jakiegokolwiek odpowiedzialności lub obciążeń finansowych, które mogą wynikać z niewłaściwego zastosowania tego produktu. Produkt musi być przechowywany, transportowany i aplikowany zgodnie z zaleceniami Rust-Oleum. Użytkownik powinien zadbać o posiadanie najbardziej aktualnej karty produktu. Wszystkie karty dostępne są na stronie internetowej producenta lub dystrybutora. Firma zastrzega sobie prawo modyfikowania danych bez uprzedzenia.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu