

RUST-OLEUM®
INDUSTRIAL



METAL CLADDING TOPCOAT

Water-based satin gloss decorative topcoat

- Improves life expectancy of metal cladding
- Easy to clean and maintain
- Excellent flow and aspect with brush, roller or spray
- High filling and hiding power
- Tintable in almost any colour



KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

METAL CLADDING TOPCOAT

BESKRIVELSE

Waterborne satin gloss decorative topcoat for use on metal objects and cladding.

ANBEFALT BRUK

Finish on metal cladding or any metal surface primed with Metal Cladding Primer, PVDF Primer, NOXYDE® or PEGANOX®. Also directly onto aged Plastisol in good condition.

TEKNISKE DATA

Tetthet:	1,3
Glansgrad:	Satinert
Korrosjonsklasse:	C1/C2 lav beskyttelse
Tørrstoffinnhold i volum:	33%

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtør:	1 hour
Håndterbar:	5 hours
Overmalbar:	8 hours
Herdetid:	2 days

ANBEFALT VÅTFILMTYKKELSE

130 µm

ANBEFALT TØRRFILMTYKKELSE

45 µm

TEORETISK FORBRUK

8 m²/l

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

KLARGJØRING AV OVERFLATE

Can be applied directly on substrates primed with Metal Cladding Primer, NOXYDE® or PEGANOX®. Can also be applied on old sound paints; glossy paints will be roughed up slightly. In all cases, the substrate must be sufficiently dry and clean. Apply 1 - 2 coats of the Metal Cladding Topcoat.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PÅFØRINGSBETINGELSER

Temperature minimum 10°C / max. 80% R.H.

PÅFØRING & FORTYNNING: PENSEL

Apply undiluted in 2 coats by preference.

PÅFØRING & FORTYNNING: RULLE

Apply undiluted in 2 coats by preference. Use short nap roller.

PÅFØRING & FORTYNNING: LUFTFRI SPRØYTE

Nozzle: 013 – 015 / Pressure: 160 bar. 1 coat is sufficient in most cases, if there is no big colour difference with the previous coat. If necessary dilute with water. Check WFT and avoid over thicknesses, especially for dark colors. Too high film thickness can result in blistering.

PÅFØRING & FORTYNNING: FORSTØVNINGS-SPRØYTE

Not recommended.

RENGJØRING AV UTSTYR/SPILL

Water

MERKNADER

Do not apply in full sun or too hot conditions, to avoid a decreased flow. The product can remain a little sticky if it is used on new Plastisol cladding.

SIKKERHETSDATA

VOC nivå:	128 g/l
VOC ferdigblandet:	128 g/l
VOC kategori:	A/d
VOC grense:	130 g/l
Merknader angående sikkerhet:	Consult Material Safety Data Sheet and Safety Information printed on the can.

HOLDBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 07/02/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatablad er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu