

**RUST-OLEUM®**  
INDUSTRIAL



## METAL CLADDING TOPCOAT

# Water-based satin gloss decorative topcoat

- Improves life expectancy of metal cladding
- Easy to clean and maintain
- Excellent flow and aspect with brush, roller or spray
- High filling and hiding power
- Tintable in almost any colour



footer\_main\_page\_line\_one

footer\_main\_page\_line\_two

# METAL CLADDING TOPCOAT

## POPIS PRODUKTU (DLHÝ)

Waterborne satin gloss decorative topcoat for use on metal objects and cladding.

## ODPORÚČANÉ POUŽITIE

Finish on metal cladding or any metal surface primed with Metal Cladding Primer, PVDF Primer, NOXYDE® or PEGANOX®. Also directly onto aged Plastisol in good condition.

## TECHNICAL\_DATA

Hustota (g/cm <sup>3</sup> ):	1,3
Úroveň lesku:	Satin
Trieda korózie:	C1/C2 nízka ochrana
Obsah pevných látok v objeme:	33%

## DRY\_TIMES\_BY\_20

Na dotyk suché:	1 hour
Suché na manipuláciu:	5 hours
Suchý na opätovné natieranie:	8 hours
Úplne vytvrdnuté:	2 days

## ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

130 µm

## ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

45 µm

## TEORETICKÁ SPOTREBA

8 m<sup>2</sup>/l

## PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PRÍPRAVA POVRCHU

Can be applied directly on substrates primed with Metal Cladding Primer, NOXYDE® or PEGANOX®. Can also be applied on old sound paints; glossy paints will be roughed up slightly. In all cases, the substrate must be sufficiently dry and clean. Apply 1 - 2 coats of the Metal Cladding Topcoat.

## NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMIENKY APLIKÁCIE

Temperature minimum 10°C / max. 80% R.H.

## APLIKÁCIA A RIEDENIE: ŠTETEC

Apply undiluted in 2 coats by preference.

## APLIKÁCIA A RIEDENIE: VALEC

Apply undiluted in 2 coats by preference. Use short nap roller.

## APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Nozzle: 013 – 015 / Pressure: 160 bar. 1 coat is sufficient in most cases, if there is no big colour difference with the previous coat. If necessary dilute with water. Check WFT and avoid over thicknesses, especially for dark colors. Too high film thickness can result in blistering.

## APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Not recommended.

## ČISTENIE ZARIADENIA / POSTRIEKANIE

Water

## POZNÁMKY

Do not apply in full sun or too hot conditions, to avoid a decreased flow. The product can remain a little sticky if it is used on new Plastisol cladding.

## DATA SAFETY DATA

Úroveň VOC:	128 g/l
VOC readymix:	128 g/l
Kategória VOC:	A/d
Limit VOC:	130 g/l
Poznámky k bezpečnosti:	Consult Material Safety Data Sheet and Safety Information printed on the can.

## SKLADOVATEĽNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last\_updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu