




NOXYDE® PLUS



Ultimate water-based corrosion protection

- Superior adhesion
- Flexible one pack coating
- High dirt pick up resistance
- 200% elastic coat does not crack or peel
- Excellent coverage of nuts, bolts and welds

footer_main_page_line_one

footer_main_page_line_two

NOXYDE® PLUS

POPIS PRODUKTU (DLOUHÝ)

Single pack water-based elastomeric coating based on a silane modified acrylic binder with superior adhesion and corrosion protection. The product contains anti-corrosion pigments and is lead, chromate and zinc free.

DOPORUČENÉ POUŽITÍ

1. On iron, steel, special alloys, galvanised and metallised iron and steel, aluminium, copper, zinc, lead, etc. as rust prevention or waterproofing. For outside and inside use.
2. Diluted with 25% water as an adhesion primer coat on slightly or non porous substrates such as glass, smooth bricks and concrete, ceramics, tiles, etc.

TECHNICAL DATA

Hustota (g/cm ³):	1,25
Úroveň lesku:	Satin
Úroveň lesku při 60°:	24%
Obsah pevných látek v hmotnosti:	66%
Obsah pevných látek v objemu:	46%
Odolnost proti solné mlze:	1.248h salt spray resistance ISO 9227:2017

DRY_TIMES_BY_20

Dotykem suché:	1hr and 20 minutes
Suché na manipulaci:	2 hours and 45 minutes
Suchý náter:	24 hours
Plně vytvrzené:	2 weeks

DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

380 µm

DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

175 µm

TEORETICKÁ SPOTŘEBA

Brush/Roller - 240 - 360 g/m²/coat
Airless - 360 - 600 g/m²/coat
Total consumption for optimal rust preventive protection 950 g/m² (in minimum 2 coats) = 350 µm dry film thickness

PRAKTIČKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PŘÍPRAVA POVRCHU

Remove grease, oil and all other surface contaminations by alkaline or high pressure (steam) cleaning (max. 200 Bars) in combination with appropriate detergents. The substrate has to be dust free and made rust free by means of sandblasting (Sa2), manual cleaning (St2) or high pressure water jetting (min. 600 Bars). After jetting, the substrate has to be dust free. On new galvanised surfaces, new zinc, aluminium, stainless steel, apply first a coat of Pegalink or PVDF Primer. On ferrous substrates, apply Noxyde Plus in red or grey as the first coat. In all instances apply contrasting Noxyde Plus colours for subsequent layers.

NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred mechanically prior to use.

PODMÍNKY POUŽITÍ

Temperature of air, substrate and coating material between 8 and 35°C.

Air humidity max. 80% R.H.

The substrate temperature must be at least 5°C above dew point.

APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Undiluted as a rust preventive paint. Diluted with up to 25% volume water as an adhesion primer (consumption about 120 g/m² - max. 100 µm wet film thickness - 20 µm dry film thickness)

APLIKACE A ŘEDĚNÍ: VÁLEČEK

Undiluted as a rust preventive paint. Diluted with up to 25% volume water as an adhesion primer (consumption about 120 g/m² - max. 100 µm wet film thickness - 20 dry film thickness)

APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

Undiluted. Nozzle: 15 - 19 / Pressure: min. 170 bars. Nozzle and pressure can vary depending on the type of substrate, equipment and the experience of the applicator. Put a thin layer of water on top of the paint to prevent skinning.

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Water

POZNÁMKY

When used for interior works, provide for adequate ventilation. during work stoppage, fully immerse brush or nozzle in water. Product is recoatable after 24 hours with itself.

Compatible topcoats: Coating PRT, Alkythane 7500, Metal Cladding Topcoat, Paracem range, Pegacryl Satin.

Do not apply outside if rain is expected within 24 hours.

Maximum wet film thickness: 600µm.

For any information regarding options of guarantee with this system, please contact Technical Service.

DATA_SAFETY_DATA

Úroveň těkavých organických

látek:	45g/l
VOC readymix:	45g/l
Kategorie VOC:	A/i
Limitní hodnota VOC:	140g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

DOBA POUŽITELNOSTI

Minimum of 4 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu