

**RUST-OLEUM®**  
INDUSTRIAL



**NS200/300/500**

## Anti-slip additives for 2K paints



- Durable aluminium oxide anti-slip additive
- Resists vehicular traffic
- Choice of 3 different granule sizes
- Can be pre-mixed or broadcasted over wet paint
- For any 2K paint

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# NS200/300/500

## BESKRIVNING

Anti-slip granulates, made of thermally split flint stones, turn a standard floor coating into a durable anti-slip coating.

## REKOMMENDERAD ANVÄNDNING

Non-Skid 200, 300 & 500 Additives are intended to be added to floor coatings to produce a non-skid surface. Anti-slip additives can be used in combination with the following RUST-OLEUM 2K-Floor coatings: 5500, 9100, Pegakote, 5800, 9700 and Rust-O-Thane® Polyurethane Topcoats. Non-Skid Additives can be mixed with the required RUST-OLEUM coating system or can be sprinkled into the freshly applied coating manually or with special low pressure spraying equipment. Intended for Non-Skid industrial flooring and should be topcoated with the required RUST-OLEUM System if sprinkled.

## TEKNISK DATA

Densitet:	2,3
Torrsubstansvikt:	100%
Torrsubstansvolym:	100%

## TEORETISK FÖRBRUKNING

NS200/300: Sparingly: 20 m<sup>2</sup>/kg (= 200 g/l if mixed in), Dense: 10 m<sup>2</sup>/kg (= 400 g/l if mixed in)

NS500: Sparingly: 5 m<sup>2</sup>/kg, Dense: 2 m<sup>2</sup>/kg.

## PRAKTISK FÖRBRUKNING

Practical usage depends on many factors such as type and amount of contaminants, shape of the substrate and material losses during application.

## BRUKSANVISNING

Sprinkling: sprinkle the granulates onto the freshly applied, wet RUST-OLEUM coating, manually with a "sprinkler-box" for small areas, or with special low-pressure spraying equipment with a nozzle opening of at least 18 mm ; air pressure between 1 - 3 bars.

Mixing: mix the granulates into the wet coating material and apply the coating with a roller or a brush (not by spraying), stir regularly to avoid settling of the granulates.

## APPLICERINGSFÖRHÅLLANDEN

For optimum results, follow the application conditions with the applied RUST-OLEUM Floor Coating.

## ANMÄRKNINGAR

For coating systems with a dry film thickness less than 300 µm it is recommended to use NS 200. For 1K-paints, use NS100.

Particle size: NS200: 0.2 - 0.5 mm, NS300: 0.5 - 1.0 mm, NS500: 0.8 - 1.5 mm. NS500 is available in white (aluminium oxide) and black (carborundum/iron oxide) - use white for light coating colours and black for darker coating colours.

## HÅLLBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivet den: 07/02/2025

**Tillgängliga färger och förpackningsstorlekar**: Se respektive produktsida på [www.rust-oleum.eu](http://www.rust-oleum.eu) för en översikt över tillgängliga färger och förpackningsstorlekar.

**Förbehåll**: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från [www.rust-oleum.eu](http://www.rust-oleum.eu) eller vår Kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaper i sina produkter utan föregående avisering.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)