

**RUST-OLEUM®**  
INDUSTRIAL



**PEGACRETE®**

## Water-based cementitious repair

- Stronger than concrete
- Easy to apply: just add water and stir
- Can be recoated with all paint types
- Low odour
- For indoor and outdoor use



KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# PEGACRETE®

## BESKRIVELSE

Powdered repair product for leveling and repairing cracks, holes and other damages in concrete, cement renderings and non-painted brickwork.

## ANBEFALT BRUK

For indoor and outdoor works, for levelling and repairing cracks, holes and other damages in concrete, cement renderings and not painted brickwork.

## TEKNISKE DATA

Tetthet: 1,6  
Trykkfasthet: 38 MN/m<sup>2</sup>  
Strekfasthet: 38 MN/m<sup>2</sup>  
Blandeforhold: Pegacrete : Water = 5kg : 1L

## TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Overmalbar: 2 days  
Herdetid: 1 month

## ANBEFALT VÅTFILMTHYKKELSE

2 cm

## ANBEFALT TØRRFILMTHYKKELSE

2 cm

## TEORETISK FORBRUK

Maximum 32 kg/m<sup>2</sup> per layer at 2 cm thickness.

## PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## KLARGJØRING AV OVERFLATE

On bare substrate: clean with steel brush or sand blaster. The substrate must be solid and free from dust, oil and grease. Porous substrates must be moistened first. Metal parts are to be treated with NOXYDE.

## BRUKSANVISNING

Add Pegacrete progressively to water and mix steadily.

## PÅFØRINGSBETINGELSER

Apply at a temperature of minimum 5°C.

## PÅFØRING & FORTYNNING: RAKE/MURSKJE

Filling blade or trowel.

## RENGJØRING AV UTSTYR/SPILL

Water

## MERKNADER

Do not use more water than necessary for the application. Pegacrete must be applied with a coat thicknesses of 5-20 mm. For thicker coats (20 mm and more) it is preferable to add some sand to the mortar in the following proportion: for 1 litre of mortar, 0,3 till 0,5 litre of sand 0-4 mm.

## SIKKERHETSDATA

VOC nivå: 0 g/l  
grenelle: c  
Merknader angående sikkerhet: Consult Safety Data Sheet and Safety Information printed on the can.

## HOLDBARHET

Minimum of 1 year from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 07/02/2025

**Tilgjengelige farger & størrelse på forpakninger:** Vennligst referer til den respektive produktsiden på [www.rust-oleum.eu](http://www.rust-oleum.eu) for en oversikt over tilgjengelige farger og størrelse på forpakninger.

**Ansvarsfraskrivelse:** Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatablad er tilgjengelig, og kan lastes ned gratis fra [www.rust-oleum.eu](http://www.rust-oleum.eu), eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu