

RUST-OLEUM®
INDUSTRIAL



PEGACRETE®

Water-based cementitious repair

- Stronger than concrete
- Easy to apply: just add water and stir
- Can be recoated with all paint types
- Low odour
- For indoor and outdoor use



footer_main_page_line_one

footer_main_page_line_two

PEGACRETE®

POPIS PRODUKTU (DLHÝ)

Powdered repair product for levelling and repairing cracks, holes and other damages in concrete, cement renderings and non-painted brickwork.

ODPORÚČANÉ POUŽITIE

For indoor and outdoor works, for levelling and repairing cracks, holes and other damages in concrete, cement renderings and not painted brickwork.

TECHNICAL DATA

Hustota (g/cm³): 1,6
Pevnosť v tlaku: 38 MN/m²
Pevnosť v ťahu: 38 MN/m²
Pomer miešania: Pegacrete : Water = 5kg : 1L

DRY TIMES BY 20

Suchý na opätovné natieranie: 2 days
Úplne vytvrdnuté: 1 month

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

2 cm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

2 cm

TEORETICKÁ SPOTREBA

Maximum 32 kg/m² per layer at 2 cm thickness.

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

On bare substrate: clean with steel brush or sand blaster. The substrate must be solid and free from dust, oil and grease. Porous substrates must be moistened first. Metal parts are to be treated with NOXYDE.

NÁVOD NA POUŽITIE

Add Pegacrete progressively to water and mix steadily.

PODMIENKY APLIKÁCIE

Apply at a temperature of minimum 5°C.

APLIKÁCIA A RIEDENIE: HRABLAMI/HRABLIČKOU

Filling blade or trowel.

ČISTENIE ZARIADENIA / POSTRIEKANIE

Water

POZNÁMKY

Do not use more water than necessary for the application. Pegacrete must be applied with a coat thicknesses of 5-20 mm. For thicker coats (20 mm and more) it is preferable to add some sand to the mortar in the following proportion: for 1 litre of mortar, 0,3 till 0,5 litre of sand 0-4 mm.

DATA SAFETY DATA

Úroveň VOC: 0 g/l
Grenelle: C
Poznámky k bezpečnosti: Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATELNOSŤ

Minimum of 1 year from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chiène
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu