

RUST-OLEUM®
INDUSTRIAL



PEGACRETE®

Water-based cementitious repair

- Stronger than concrete
- Easy to apply: just add water and stir
- Can be recoated with all paint types
- Low odour
- For indoor and outdoor use



KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

PEGACRETE®

BESKRIVNING

Powdered repair product for leveling and repairing cracks, holes and other damages in concrete, cement renderings and non-painted brickwork.

REKOMMENDERAD ANVÄNDNING

For indoor and outdoor works, for levelling and repairing cracks, holes and other damages in concrete, cement renderings and not painted brickwork.

TEKNISK DATA

Densitet: 1,6
Tryckhållfasthet: 38 MN/m²
Draghållfasthet: 38 MN/m²
Blandningsförhållande: Pegacrete : Water = 5kg : 1L

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Övermålningsbar: 2 days
Fullt härdad: 1 month

REKOMMENDERAD VÅTFILMSTJOCKLEK

2 cm

REKOMMENDERAD TORRFILMSTJOCKLEK

2 cm

TEORETISK FÖRBRUKNING

Maximum 32 kg/m² per layer at 2 cm thickness.

PRAKTISK FÖRBRUKNING

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

YTFÖRBEREDELSE

On bare substrate: clean with steel brush or sand blaster. The substrate must be solid and free from dust, oil and grease. Porous substrates must be moistened first. Metal parts are to be treated with NOXYDE.

BRUKSANVISNING

Add Pegacrete progressively to water and mix steadily.

APPLICERINGSFÖRHÅLLANDEN

Apply at a temperature of minimum 5°C.

APPLICERING OCH SPÄDNING: RAKA/SLEV

Filling blade or trowel.

RENGÖRING AV UTRUSTNING/SPILL

Water

ANMÄRKNINGAR

Do not use more water than necessary for the application. Pegacrete must be applied with a coat thicknesses of 5-20 mm. For thicker coats (20 mm and more) it is preferable to add some sand to the mortar in the following proportion: for 1 litre of mortar, 0,3 till 0,5 litre of sand 0-4 mm.

SÄKERHETSDATA

VOC-nivå: 0 g/l
grenelle: c
Anmärkningar om säkerhet: Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET

Minimum of 1 year from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivet den: 07/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdskador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår Kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu