

RUST-OLEUM®
INDUSTRIAL



NOXYDE® PEGANOX

Single pack water-based elastic coating



- Good corrosion protection and waterproofing
- Smooth aesthetic satin finish
- 200% elastic coat does not crack or peel
- Excellent flow, ideal for roller/brush application
- Primer and topcoat in one

footer_main_page_line_one

footer_main_page_line_two

NOXYDE® PEGANOX

POPIS PRODUKTU (DLHY)

Single pack water-based elastic coating, optimized for brush or roller application.

ODPORÚČANÉ POUŽITIE

Anticorrosive protection on ferrous and non-ferrous metals.

TECHNICAL DATA

Hustota (g/cm ³):	1,2
Úroveň lesku:	Satin
Trieda korózie:	C4 vysoká ochrana
Obsah pevných látok v hmotnosti:	58%
Obsah pevných látok v objeme:	48%

DRY TIMES BY 20

Na dotyk suché:	1 hour
Suché na manipuláciu:	2 hours
Suchý na opätovné natieranie:	6 hours
Úplne vytvrdnuté:	2 days

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

165 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

80 µm

TEORETICKÁ SPOTREBA

2 coats of minimum 200 g/m² (5 m²/kg)

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

Apply the usual derusting procedures (min. Sa 2 sand blasting, min. St 2 steel brush, etc.) or by high-pressure water (min. 600 bars). Dedust well after sand blasting.

NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE

Temperature between 8 and 55°C. Air humidity max. 80% R.H. The substrate temperature must be at least 5°C above dew point.

APLIKÁCIA A RIEDENIE: ŠTETEC

Apply undiluted.

APLIKÁCIA A RIEDENIE: VALEC

Apply undiluted.

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Nozzle: 11 - 13 / Pressure: 220 bars.

Diluted with maximum 3% volume of water.

APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Apply undiluted.

CISTENIE ZARIADENIA / POSTRIEKANIE

Water

POZNÁMKY

When used inside, provide for adequate ventilation.

During work stoppage, fully immerse brush or nozzle in water, empty and clean the tubes.

On non-ferrous substrates, use PVDF Primer or Pegalink as adhesion primer first.

For any information regarding options of guarantee with this system, please contact Technical Service.

DATA SAFETY DATA

Úroveň VOC:	15 g/l
VOC readymix:	15 g/l
Kategória VOC:	A/i
Limit VOC:	140 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATEĽNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 31/10/2024

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM s-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu