

RUST-OLEUM®
INDUSTRIAL



PEGASOL® QUARTZ

Durable anti-slip coating.

- Durable Quartz finish
- Easy application
- Fast drying
- Abrasion resistant
- Odourless

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

PEGASOL® QUARTZ

DESCRIZIONE

Two-pack water based anti-slip floor coating for indoor and outdoor application.

UTILIZZO CONSIGLIATO

For external works: on balconies, terraces, etc. For inside works: on industrial floors, warehouses, (in garages, a top coat in Pegakote has to be applied on Pegasol Quartz).

DATI TECNICI

Densità:	1,6
Livello di lucentezza:	Satinato
Residuo secco in peso:	77%
Residuo secco in volume:	63%
Rapporto di miscelazione:	Base : Activator = 7 : 0.5 (Weight)

TEMPI DI ASCIUGATURA A 20°C/UR 50%

Asciutto al tatto:	45 minutes
Asciutto da maneggiare:	2 hours
Asciutto da rivestire:	6 hours
Completamente indurito:	1 week
Durata del contenitore:	1 hour (12 hours when diluted with 5% volume water)

SPESSORE DELLA PELLICOLA UMIDA CONSIGLIATO

500 µm (800 g/m²)

SPESSORE DELLA PELLICOLA ASCIUTTA CONSIGLIATO

315 µm

CONSUMO TEORICO

800 g/m² per coat

CONSUMO PRATICO

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PREPARAZIONE DELLA SUPERFICIE

The substrate should be clean, dry and free from rising ground water. Pegasol Quartz can be applied directly on tiles, ceramics (even glazed), non-porous natural stones, tarmacadam. Porous concrete must be impregnated first with Primer 44 HS or with Vernac diluted with 10% volume Thinner 22. Curing compounds in case of poly concrete have to be removed by sand or grit blasting. On new or non-porous concrete, remove the cement grout by sand or grit blasting or attack with diluted hydrochloric acid (3 l hydrochloric acid in 10 l water, let it act for 10 minutes and rinse abundantly with clear water), let it dry a few days before application.

ISTRUZIONI PER L'USO

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

CONDIZIONI DI APPLICAZIONE

Minimum 8°C, maximum 80% R.H.

APPLICAZIONE E DILUIZIONE: PENNELLO

Apply undiluted by preference.

APPLICAZIONE E DILUIZIONE: RULLO

Apply undiluted by preference.

APPLICAZIONE E DILUIZIONE: SPRAY SENZ'ARIA

Not recommended.

APPLICAZIONE E DILUIZIONE: SPRAY AD ARIA-ATOMIZZATA

Not recommended.

PULITURA DELLE ATTREZZATURE / DEGLI SVERSAMENTI

Water

NOTE

- Pegasol Quartz will withstand foot traffic after 6 hours and wheeled traffic after 3 days
- Because of the development of acid products in Pegasol (Quartz) under influence of UV-rays, it should not be finished with polyurethane-varnishes (e.g. Pegagraff Hydro) in case of external works
- Add the hardener to the base gradually with good mechanical stirring
- When Pegasol Quartz has to be recoated, please contact our Technical Service
- For applications on balconies and terraces, please contact our Technical Service.

DATI RELATIVI ALLA SICUREZZA

Livello di COV:	30 g/l
Soluzione premiscelata COV:	30 g/l
Categoria COV:	A/j
Limite di COV:	140 g/l
Note riguardanti la sicurezza:	Consult Safety Data Sheet and Safety Information printed on the can.

SCADENZA

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Data del rilascio: 07/02/2025

Colori e formati di confezione disponibili: Si prega di consultare la pagina relativa al prodotto su www.rust-oleum.eu per una visione complessiva dei colori e dei formati di confezione effettivamente disponibili.

Dichiarazione di non responsabilità: Le informazioni contenute nel presente documento sono al meglio della nostra conoscenza, vere e accurate e sono fornite in buona fede ma senza garanzia. L'utente sarà ritenuto soddisfatto/a indipendentemente dall'idoneità dei nostri prodotti per il suo proprio scopo particolare. In nessun caso Rust-Oleum Europe potrà essere ritenuta responsabile per danni consequenziali o incidentali. I prodotti devono essere conservati, maneggiati e applicati in condizioni conformi alle raccomandazioni dettagliate di Rust-Oleum Europe contenute nella copia più recente della scheda tecnica del prodotto. È responsabilità dell'utente accertarsi di disporre della copia attuale. Le copie più recenti della scheda tecnica del prodotto sono disponibili gratuitamente e scaricabili da www.rust-oleum.eu o a fronte di richiesta al nostro servizio clienti. Rust-Oleum Europe si riserva il diritto di modificare le proprietà dei suoi prodotti senza alcun preavviso.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu