

**RUST-OLEUM®**  
INDUSTRIAL



## PEGASOL® QUARTZ

# Durable anti-slip coating.

- Durable Quartz finish
- Easy application
- Fast drying
- Abrasion resistant
- Odourless

footer\_main\_page\_line\_one

footer\_main\_page\_line\_two

# PEGASOL® QUARTZ

## POPIS PRODUKTU (DLHÝ)

Two-pack water based anti-slip floor coating for indoor and outdoor application.

## ODPORÚČANÉ POUŽITIE

For external works: on balconies, terraces, etc. For inside works: on industrial floors, warehouses, (in garages, a top coat in Pegakote has to be applied on Pegasol Quartz).

## TECHNICAL DATA

Hustota (g/cm <sup>3</sup> ):	1,6
Úroveň lesku:	Satin
Obsah pevných látok v hmotnosti:	77%
Obsah pevných látok v objeme:	63%
Pomer miešania:	Base : Activator = 7 : 0.5 (Weight)

## DRY TIMES BY 20

Na dotyk suché:	45 minutes
Suché na manipuláciu:	2 hours
Suchý na opätovné natieranie:	6 hours
Úplne vytvrdnuté:	1 week
Život v hrci:	1 hour (12 hours when diluted with 5% volume water)

## ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

500 µm (800 g/m<sup>2</sup>)

## ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

315 µm

## TEORETICKÁ SPOTREBA

800 g/m<sup>2</sup> per coat

## PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PRÍPRAVA POVRCHU

The substrate should be clean, dry and free from rising ground water. Pegasol Quartz can be applied directly on tiles, ceramics (even glazed), non-porous natural stones, tarmacadam. Porous concrete must be impregnated first with Primer 44 HS or with Vernac diluted with 10% volume Thinner 22. Curing compounds in case of poly concrete have to be removed by sand or grit blasting. On new or non-porous concrete, remove the cement grout by sand or grit blasting or attack with diluted hydrochloric acid (3 l hydrochloric acid in 10 l water, let it act for 10 minutes and rinse abundantly with clear water), let it dry a few days before application.

## NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMIENKY APLIKÁCIE

Minimum 8°C, maximum 80% R.H.

## APLIKÁCIA A RIEDENIE: ŠTETEC

Apply undiluted by preference.

## APLIKÁCIA A RIEDENIE: VALEC

Apply undiluted by preference.

## APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Not recommended.

## APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Not recommended.

## ČISTENIE ZARIADENIA / POSTRIEKANIE

Water

## POZNÁMKY

- Pegasol Quartz will withstand foot traffic after 6 hours and wheeled traffic after 3 days
- Because of the development of acid products in Pegasol (Quartz) under influence of UV-rays, it should not be finished with polyurethane-varnishes (e.g. Pegagraff Hydro) in case of external works
- Add the hardener to the base gradually with good mechanical stirring
- When Pegasol Quartz has to be recoated, please contact our Technical Service
- For applications on balconies and terraces, please contact our Technical Service.

## DATA SAFETY DATA

Úroveň VOC:	30 g/l
VOC readymix:	30 g/l
Kategória VOC:	A/j
Limit VOC:	140 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

## SKLADOVATELNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last\_updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chiène  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu