

RUST-OLEUM®
INDUSTRIAL



SURFA-ETCH® 108

Etching solution for floors and metal

- Improves the adhesion of coating systems
- Neutralizes alkaline salts
- Also ideal to remove 'white rust' from metal
- No objectionable odour or fumes
- Non-flammable

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

SURFA-ETCH® 108

DESCRIZIONE

Etching solution for etching smooth concrete surfaces, masonry, galvanized steel and aluminum before applying a coating system.

UTILIZZO CONSIGLIATO

Surfa-Etch 108 Etching Solution should be used for etching smooth concrete surfaces, masonry, galvanised steel and aluminium before applying a RUST-OLEUM coating system. Surfa-Etch 108 neutralizes alkaline contaminations and removes zinc- and aluminium corrosion products ("white rust") Surfa-Etch 108 should be applied with a stiff nylon brush or a broom.

CONSUMO TEORICO

6 - 8 m²/l

CONSUMO PRATICO

Practical usage depends on many factors such as type and amount of contaminants, shape of the substrate and material losses during application.

ISTRUZIONI PER L'USO

To ensure homogeneity shake well before use. Scrape or sweep away grease, oil, dirt and all other surface contaminations as much as possible. Degrease by means of alkaline cleaning, high pressure (steam) cleaning or, for small patches, by volatile solvent cleaning. Apply Surfa-Etch 108 Etching Solution liberally and scrub it into the surface. Allow to stand for 10-15 minutes, depending on temperature, and clean thoroughly by flushing with plenty of fresh water. Do not allow the Surfa-Etch 108 Etching Solution to dry before rinsing Concrete and masonry may need a second treatment. After cleaning, remove any remaining water and allow to dry completely, as moisture left on the surface or entrapped into pores may cause failure of the coating system. Large surface areas or poor drying conditions may require longer drying times before a coating system can be applied.

CONDIZIONI DI APPLICAZIONE

Temperature of air, substrate and material between 5 and 35°C.

DATI RELATIVI ALLA SICUREZZA

Livello di COV: 45 g/l
Note riguardanti la sicurezza: Consult Safety Data Sheet and Safety Information printed on the can.

PH

1

SCADENZA

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Data del rilascio: 07/02/2025

Colori e formati di confezione disponibili: Si prega di consultare la pagina relativa al prodotto su www.rust-oleum.eu per una visione complessiva dei colori e dei formati di confezione effettivamente disponibili.

Dichiarazione di non responsabilità: Le informazioni contenute nel presente documento sono al meglio della nostra conoscenza, vere e accurate e sono fornite in buona fede ma senza garanzia. L'utente sarà ritenuto soddisfatto/a indipendentemente dall'idoneità dei nostri prodotti per il suo proprio scopo particolare. In nessun caso Rust-Oleum Europe potrà essere ritenuta responsabile per danni consequenziali o incidentali. I prodotti devono essere conservati, maneggiati e applicati in condizioni conformi alle raccomandazioni dettagliate di Rust-Oleum Europe contenute nella copia più recente della scheda tecnica del prodotto. È responsabilità dell'utente accertarsi di disporre della copia attuale. Le copie più recenti della scheda tecnica del prodotto sono disponibili gratuitamente e scaricabili da www.rust-oleum.eu o a fronte di richiesta al nostro servizio clienti. Rust-Oleum Europe si riserva il diritto di modificare le proprietà dei suoi prodotti senza alcun preavviso.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu