

RUST-OLEUM[®]
— INDUSTRIAL —



SPEED PATCH POURABLE GRADE

Quick setting, pourable repair product.

- Accepts heavy traffic 2 hours after application
- Easy to prepare: add water and mix
- Possible to apply on slightly wet concrete
- Sets at low temperatures (5 °C)
- For deep or shallow repairs



KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

SPEED PATCH POURABLE GRADE

ОПИСАНИЕ

Speed Patch Pourable is an easy to mix pourable material for quick repairs to level concrete, inside or outside. NOTE: This product is only available in the UK.

ПРЕПОРЪЧАНА УПОТРЕБА

Repairs of heavily trafficked floors.

ТЕХНИЧЕСКИ ДАННИ

group_repair_30_compressive_strength_MPa

Степен на смесване: Powder : Water = 3 : 1 (Volume)

ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух за употреба: 2 h

Напълно втвърден: 24 h

Живот в гърне: 5 - 10 min

РАЗХОДНА НОРМА

As a guide, each unit of 25 kg will cover approximately 0.5 m² at 25 mm thick.

КОНСУМАЦИЯ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

ПОДГОТОВКА НА ПОВЪРХНОСТТА

The substrate should be clean and free from oil or contaminants. Any loose material should be removed from the surface. If possible wire brush the surface. Edges of the repair should be cut to depth to avoid feather-edging in heavy wear areas. Speed Patch Pourable can be applied to damp (not wet) concrete.

НАЧИН НА УПОТРЕБА

Remove the bag of powder from the plastic bucket and use the empty bucket or other suitable container for mixing. Due to the short working life of the mixed product, we recommend you carry out the mixing near to the repair, not near to the water source. It's also useful to have a bucket of water nearby, so you can quickly immerse and clean the tools after use. Put the water into the empty bucket or container and gradually add the powder stirring constantly to achieve a pourable slurry. For small quantities mix by hand using a flat bladed tool such as a spatula, and for larger quantities use a mixer fitted into a slow speed electric drill. Do not add excessive water or drying time will be extended and the performance may be impaired. As the mixture hardens quickly, pour the Speed Patch Pourable into the hole to be repaired immediately. We do not recommend re-stirring as this could potentially weaken the final repair.

УСЛОВИЯ ЗА НАНАСЯНЕ

Apply at a temperature of approximately 5°C - 20°C. Do not apply at less than 5°C.

GROUP_APPL_THINNING_50_RAKE_TROWEL

When a smooth consistency is achieved, simply pour Speed Patch in to the hole. If the product has been properly mixed it will self-level and will need minimal trowelling. Speed Patch Pourable can be applied in any depth between 5 mm and 100 mm. Repairs in lightly trafficked areas can be feather edged, but thin edges are not recommended for medium or heavily trafficked repairs.

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Remove excess with a cloth or scraper and wash with water before the product sets.

ЗАБЕЛЕЖКИ

Temperatures below 10°C will delay the curing process. As a guide, allow 24 hours when applied at 5°C. Do not apply at temperatures below 0°C. Speed Patch Pourable can be applied at any depth between 5 - 100 mm and repairs can be feather edged in light traffic areas. When mixed, this product will be pourable so is not suitable for repairs to sloping floors or exposed edges. After curing the product can be painted with any suitable floor paint. If the floor being repaired is very rough, you may wish to screed the whole floor for a smooth flat surface before painting.

СРОК НА ГОДНОСТ

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Дата на издаване: 20/03/2025

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu