

RUST-OLEUM®
INDUSTRIAL



SUPERGRIP® 1K ANTI-SLIP FLOOR COATING



Easy to apply 1 component anti-slip floor coating

- For foot traffic, interior and exterior
- Anti-slip additive is premixed in the coating
- For use on old concrete (>2yrs), metal and wood
- Touch dry after 6 hours

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

SUPERGRIP® 1K ANTI-SLIP FLOOR COATING

DESCRIZIONE

Easy to apply solvent based Alkyd anti-slip floor coating specially designed for applying on old (>2 years), dry concrete for interior and exterior use. The coating has a good resistance against abrasion and neutral detergents (no alkaline cleaning agents) and is resistance during short contact periods against lubricating oils, fuel, petrol etc.

UTILIZZO CONSIGLIATO

7100 Floor Coating can be applied on concrete floors older than 2 years, which are completely clean and dry. It is not recommended to apply on smooth/dense concrete or concrete containing a damp repellent additive, which will prevent a good adhesion. 7100 Floor Coating can also be applied on old good adhering coatings. 7100 can be applied onto metal floors which have been correctly prepared and primed with a suitable Rust-Oleum metal primer.

DATI TECNICI

Densità: 1,0 -1,1
Livello di lucentezza: Lucido
Residuo secco in volume: 36 - 40%

TEMPI DI ASCIUGATURA A 20°C/UR 50%

Asciutto al tatto: 6 hours
Asciutto da rivestire: 24 hours
Completamente indurito: 1 week

SPESSORE DELLA PELLICOLA UMIDA CONSIGLIATO

130 µm

SPESSORE DELLA PELLICOLA ASCIUTTA CONSIGLIATO

50 µm

CONSUMO TEORICO

8,0 m²/l at 50 µm dry

CONSUMO PRATICO

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PREPARAZIONE DELLA SUPERFICIE

Remove oil, grease and other contaminations with Rust-Oleum 2901 EpoxyShield Cleaner/Degreaser for floors or high pressure- (steam) cleaning in combination with appropriate detergents. Sand old intact coatings to roughen the surface in order to establish a good adhesion. Check the compatibility with old intact coatings. During application the surface should be dry and clean. On porous concrete a first coat should be applied with 7100 diluted with ±10% volume 7301. Remove curing compounds by means of dust free blasting.

ISTRUZIONI PER L'USO

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

CONDIZIONI DI APPLICAZIONE

Apply in a dry and well-ventilated area.

APPLICAZIONE E DILUIZIONE: PENNELLO

Sparingly, if required, with 10% volume 7301.

APPLICAZIONE E DILUIZIONE: RULLO

Sparingly, if required, with 10% volume 7301. In case of roller application it can be necessary to apply 2 coats in order to obtain the recommended film thickness.

PULITURA DELLE ATTREZZATURE / DEGLI SVERSAMENTI

Immediately after application using 7301.

NOTE

Apply 7100 Floor Coating never on alkaline substrates.
Not suitable for use on tiles and in wet areas such as bathrooms.

DATI RELATIVI ALLA SICUREZZA

Livello di COV: 456 g/l
Soluzione premiscelata COV: 485 g/l
Categoria COV: A/i
Limite di COV: 500 g/l
Note riguardanti la sicurezza: Consult Safety Data Sheet and Safety Information printed on the can.

SCADENZA

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Data del rilascio: 07/02/2025

Colori e formati di confezione disponibili: Si prega di consultare la pagina relativa al prodotto su www.rust-oleum.eu per una visione complessiva dei colori e dei formati di confezione effettivamente disponibili.

Dichiarazione di non responsabilità: Le informazioni contenute nel presente documento sono al meglio della nostra conoscenza, vere e accurate e sono fornite in buona fede ma senza garanzia. L'utente sarà ritenuto soddisfatto/a indipendentemente dall'idoneità dei nostri prodotti per il suo proprio scopo particolare. In nessun caso Rust-Oleum Europe potrà essere ritenuta responsabile per danni consequenziali o incidentali. I prodotti devono essere conservati, maneggiati e applicati in condizioni conformi alle raccomandazioni dettagliate di Rust-Oleum Europe contenute nella copia più recente della scheda tecnica del prodotto. È responsabilità dell'utente accertarsi di disporre della copia attuale. Le copie più recenti della scheda tecnica del prodotto sono disponibili gratuitamente e scaricabili da www.rust-oleum.eu o a fronte di richiesta al nostro servizio clienti. Rust-Oleum Europe si riserva il diritto di modificare le proprietà dei suoi prodotti senza alcun preavviso.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu