

RUST-OLEUM®
— INDUSTRIAL —



SUPERGRIP™ TREADSAFE WB

- Waterbased antislip epoxy resin
- Fast drying: 2 coats in 1 day
- Ceramic additives
- Low maintenance, hard wearing floor finish
- low VOC-level

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

SUPERGRIP™ TREADSAFE WB

BESKRIVELSE

SuperGrip™ TreadSafe WB is a 'Best in Class' water based, anti slip epoxy resin. This tough, easy to use coating dries faster to reduce downtime and lasts longer to save recoating costs. The rapid drying formula also allows the application of 2 coats in one day. Our unique blend of the best resins available with a 'diamond hard' wax and ceramic additive provide an attractive, low maintenance, hard wearing floor finish which lasts and lasts

ANBEFALET BRUG

Best results are obtained in warm (minimum 15°C), dry conditions with good ventilation. In very high temperatures (30°C and above) it is recommended that bare concrete is lightly dampened first with water. Apply with a medium pile roller, working well into the surface of the concrete. Occasional stirring will ensure a more even distribution of the aggregate. Do not exceed the maximum coverage of 30m² per 5 litre pack, per coat. The product will darken slightly as curing commences and it should not be over rolled. The second coat can be applied as soon as the first coat is dry (generally 4-6 hours) and should be applied within 5 days. If more than 5 days elapse, the first coat should be lightly abraded before the second coat is applied. Avoid washing the surface for seven days.

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør:	2 hours
Genbehandlingstør:	4-6 hours
Fuldt hærdet:	7 days
Brugstid:	Up to 2 hours at 20°C

ANBEFALET VÅDFILMTYKKELSE

160 microns.

ANBEFALET TØRFILMTYKKELSE

100 microns.

TEORETISK FORBRUG

30m² per 5L per coat.

FORBEHANDLING AF OVERFLADEN

Bare Concrete – remove surface laitance, dust and any light dirt or grease deposits using Rust-Oleum® Surfa-Etch 108. Rust-Oleum® Surfa-Etch 108 also etches smooth, bare concrete surfaces to provide a key. Remove Rust-Oleum® Surfa-Etch 108 by thoroughly rinsing with clean water and allow surface to dry. If residual damp remains this is acceptable since SuperGrip™ TreadSafe WB is breathable.

Powerfloated or very smooth surfaces – should be used on very smooth or power floated surfaces.

New Concrete – new concrete should be left for four weeks to dry in the summer and six in the winter. The surface should then be prepared using Rust-Oleum® Surfa-Etch 108 and thoroughly rinsed away and left to dry prior to applying this coating. Highly porous surfaces – a primer may be required for high suction surfaces such as sand and cement screed. Please contact us for advice.

Painted surfaces – abrade to remove loose paint. Check remaining paint is well bonded. Very smooth, glossy paint should be lightly abraded to provide a key. MultiCleaner can be used to remove grease and oil from painted surfaces. ND14 is a very powerful degreaser for contaminated bare concrete (ND14 can soften paint.)

BRUGSANVISNING

Remove the two inner tins from the tall outer tin. Stir the contents of each tin thoroughly and pour all of the contents into the outer tin (scrape around the inside of the tins to remove any residue). Mix the components together thoroughly using a spatula or similar wide bladed tool (a piece of wooden batten is ideal). Continue mixing until an even colour and consistency are obtained. Do not mix more than one pack at a time. If a paint stirrer fitted to an electric drill is used, also use the spatula to blend in any unmixed material from the sides and bottom of the tin.

PAFØRING OG FORTYNDING: RULLE

Best results are obtained in warm (minimum 15°C), dry conditions with good ventilation. In very high temperatures (30°C and above) it is recommended that bare concrete is lightly dampened first with water. Apply with a medium pile roller, working well into the surface of the concrete. Occasional stirring will ensure a more even distribution of the aggregate. Do not exceed the maximum coverage of 30m² per 5 litre pack, per coat. The product will darken slightly as curing commences and it should not be over rolled. The second coat can be applied as soon as the first coat is dry (generally 4-6 hours) and should be applied within 5 days. If more than 5 days elapse, the first coat should be lightly abraded before the second coat is applied. Avoid washing the surface for seven days.

HOLDBARHED

24 months in unopened containers

Udstedelsesdato: 03/01/2024

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu