

**RUST-OLEUM®**  
INDUSTRIAL



## TARMACOAT™

# Versatile rapid curing acrylic floor paint

- Rain-proof and recoatable after just one hour
- Particularly suitable for tarmac, asphalt and bitumen substrates
- Can be applied on slightly damp surfaces
- Excellent resistance to U.V. and weathering
- Water-based formulation, safe to use and virtually no odour

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# TARMACOAT™

## BESKRIVELSE

Very fast-drying multi-purpose single pack acrylic water-based paint for floors and paint marking.

## ANBEFALT BRUK

As a coating on asphalt, concrete, pavement, bitumen, on parking bays for short term or intermittent use, as line marking, on tennis courts, playgrounds and many more. Not suitable for garage floors. The product will cure sufficiently in approximately 24 hours to accept light traffic (bicycle, car, etc.). In instances where occasional heavy traffic may be expected, allow 48 hours before bringing the area back into service. Cold and damp weather can have a negative effect on drying times.

## TEKNISKE DATA

Tetthet:	1,3
Glansgrad:	Matt
Glansgrad ved 60°:	10-12%
Tørrestoffinnhold i vekt:	57%
Tørrestoffinnhold i volum:	45%

## TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtør:	30 minutes
Håndterbar:	1 hour
Overmalbar:	1 hour
Herdetid:	2 days

## ANBEFALT VÅTFILMTYKKELSE

120 µm

## ANBEFALT TØRRFILMTYKKELSE

54 µm

## TEORETISK FORBRUK

4 - 8 m<sup>2</sup> per liter, depending on the type of surface.

## PRAKTISK FORBRUK

Depending on the type of surface. On Tarmac, coverage is likely to be close to 4 m<sup>2</sup>/l.

## KLARGJØRING AV OVERFLATE

Ensure the surface is clean, sound and dry (slightly damp is acceptable). Tarmacoat can be applied to existing paint providing all poorly bonded material is removed and glossy surfaces are dulled using abrasive paper. For concrete surfaces which are porous and/or have loose particles or powdering, first prime with Primer 44HS® or EpoxyShield Sealer 5220. For non-porous concrete prime with diluted NOXYDE®. For asphalt surfaces apply first a coat Tarmacoat™ 20% diluted with water.

## BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PÅFØRINGSBETINGELSER

Do not apply externally if rain or frost is forecast or if the temperature is below 10°C. Relative humidity below 85%.

## PÅFØRING & FORTYNNING: PENSEL

Apply undiluted.

## PÅFØRING & FORTYNNING: RULLE

Apply by medium pile type roller. One coat is generally sufficient although a second coat may be necessary on very porous or very rough surfaces or when a better durable system is required. Apply undiluted.

## RENGJØRING AV UTSTYR/SPILL

Clean tools in warm soapy water before the product has started to cure.

## MERKNADER

Do not apply in areas which will be constantly under water.

## SIKKERHETSDATA

VOC nivå:	40 g/l
VOC ferdigblandet:	40 g/l
VOC kategori:	A/i
VOC grense:	140 g/l
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

## HOLDBARHET

Minimum of 2 years from date of production in its sealed original packaging, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 07/02/2025

**Tilgjengelige farger & størrelse på forpakninger:** Vennligst referer til den respektive produktsiden på [www.rust-oleum.eu](http://www.rust-oleum.eu) for en oversikt over tilgjengelige farger og størrelse på forpakninger.

**Ansvarsfraskrivelse:** Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatablad er tilgjengelig, og kan lastes ned gratis fra [www.rust-oleum.eu](http://www.rust-oleum.eu), eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

### Rust-Oleum Netherlands B.V.

Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

### Tor Coatings Ltd (Rust-Oleum Industrial)

Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

### Rust-Oleum France S.A.S.

38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

### N.V. Martin Mathys S.A.

Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu