

RUST-OLEUM®
— INDUSTRIAL —



THINNER 633

Solvent based on aliphatic hydrocarbons

- Correct solvent combination for Rust-Oleum products based on alkyd resin binder
- Highly diluting capacity

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

THINNER 633

BESKRIVELSE

Highly diluting solvent based on aliphatic hydrocarbons, suitable for alkyd based coatings.

ANBEFALT BRUK

Cleaning and/or Thinning solution for the following products:

- 569 Quick drying metal primer
- 769 Damp-proof rust primer
- 1060/1080 High build metal primer
- 7200 Floorcoat PU
- 7500 Alkythane
- 8399 Hygienic Primer

PÅFØRING & FORTYNNING: PENSEL

Can be diluted up to 10% volume

PÅFØRING & FORTYNNING: RULLE

Can be diluted up to 10% volume

MERKNADER

See the Product Data sheet of the respective product for further details.

SIKKERHETSDATA

VOC nivå: 755 g/l

Merknader angående sikkerhet: Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 10/03/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatablad er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu