

RUST-OLEUM®
— INDUSTRIAL —



X1 PTFE SPRAY

A high purity, light lubricant containing PTFE

- High anti-wear characteristics
- Contains PTFE
- Water repellent
- Ultra low friction coefficient
- Temperature range: -40 °C to 120 °C

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

X1 PTFE SPRAY

OPIS

High purity, light lubricant containing PTFE. Suitable for applications requiring a clean, light film. It has outstanding lubrication and water repellent properties. reinforced with BoroTecX™. It has outstanding lubrication and water repellent properties.

ZALECANE UŻYCIE

Light duty chains, hinges, slides and gears. Ideal for air tools and other small machinery. Clean product so suitable for use in car interiors and air tools. Will lubricate garden and horticultural equipment. Ideal for use on commercial sewing and knitwear machinery.

PRZYGOTOWANIE POWIERZCHNI

Ensure electrical equipment is isolated and check surfaces for compatibility prior to application. Clean and remove old lubricant from components prior to application.

WARUNKI APLIKACJI

Apply at temperatures between 5° and 35°C.

APLIKACJA I ROZCIEŃCZANIE: AEROSOL

Shake aerosol before use. Spray a light film onto surface from 20 to 30 cm. Do not over apply.

OKRES TRWAŁOŚCI PRODUKTU

Minimum of 3 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Data wydania: 07/02/2025

Dostępne kolory i opakowania: Więcej informacji na temat dostępnych kolorów i opakowań na stronie internetowej www.rust-oleum.eu.

Zrzeczenie się: Informacje tu zawarte przekazywane są w dobrej wierze, bez udzielania gwarancji. Ponieważ warunki aplikacji są poza naszą kontrolą, Rust-Oleum nie może ponosić jakiegokolwiek odpowiedzialności lub obciążeń finansowych, które mogą wynikać z niewłaściwego zastosowania tego produktu. Produkt musi być przechowywany, transportowany i aplikowany zgodnie z zaleceniami Rust-Oleum. Użytkownik powinien zadbać o posiadanie najbardziej aktualnej karty produktu. Wszystkie karty dostępne są na stronie internetowej producenta lub dystrybutora. Firma zastrzega sobie prawo modyfikowania danych bez uprzedzenia.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu